

(54) Title of the invention : ALLOY COMPOSITION AND A METHOD OF SYNTHESIZING THE ALLOY COMPOSITION

(51) International classification :C04B0040000000, B01J0035020000, C22C0038080000, H01L0029490000, C07H0013080000

(86) International Application No Filing Date :PCT// :01/01/1900

(87) International Publication No : NA

(61) Patent of Addition to Application Number Filing Date :NA :NA

(62) Divisional to Application Number Filing Date :NA :NA

(71)**Name of Applicant :**
1)Manipal Academy of Higher Education
 Address of Applicant :Madhav Nagar, Manipal – 576104, Karnataka, India -----
Name of Applicant : NA
Address of Applicant : NA

(72)**Name of Inventor :**
1)SHARMA, Sathyashankara
 Address of Applicant :Mechanical and Industrial Engineering, Manipal Institute of Technology, Manipal Academy of Higher Education, Madhav Nagar, Manipal - 576104, Karnataka, India ---

2)NAMBIAR S, Sandeep
 Address of Applicant :Mechanical and Industrial Engineering, Manipal Institute of Technology, Manipal Academy of Higher Education, Madhav Nagar, Manipal - 576104, Karnataka, India ---

3)BRN, Murthy
 Address of Applicant :Mechanical and Industrial Engineering, Manipal Institute of Technology, Manipal Academy of Higher Education, Madhav Nagar, Manipal - 576104, Karnataka, India ---

4)PRASANNA, AA
 Address of Applicant :Physics, Malnad College of Engineering, Hassan - 573202, Karnataka, India -----

(57) Abstract :
 An alloy composition and method of synthesizing the alloy composition is disclosed. The alloy composition comprises plurality of metals Nickel in a weight percentage range of 45 % to 50%, Manganese in a weight percentage range of 29% to 31%, Tin in a weight percentage range of 10% to 20%, Indium in a weight percentage range of 2% to 10% and Iron in a weight percentage range of 1% to 5%.

No. of Pages : 18 No. of Claims : 9